



# SUPERSEAL

## 4021

### Description

SUPERSEAL 4021 is a transparent, coextured biaxially oriented polypropylene (BOPP) film. Both sides heat sealable. One side treated with standard sealing layer. Other (non-treated) sealing layer has low SIT (Seal Initiation Temperature) down to 80°C (176 °F).

Single ply and/or lamination substrate where the low SIT is needed. Specially designed for vacuum metalization applications. Metal should be coated on treated side.

It can be also used as base film for industrial applications including packaging applications where low SIT and strong heat sealability is required. It has excellent adhesion towards different ink, coating and adhesive systems including UV based.

### Properties

- Excellent wide sealing range with low SIT
- Excellent hot tack and heat seal strength
- A to B sealing capability
- Excellent ink, coating and adhesive adhesion
- Good moisture barrier
- Excellent resistance to chemicals, greases and oils

## Technical Features

PROPERTIES	TEST METHOD	UNITS	4021	
THICKNESS	ASTM F2251	micron	20	
		Gauge	80	
YIELD	ASTM D4321	m <sup>2</sup> /kg	54,9	
		in <sup>2</sup> /Lbs	38.600	
UNIT WEIGHT	ASTM D4321	g/m <sup>2</sup>	18,2	
HAZE	ASTM D1003	%	3,0	
GLOSS (45 °)	ASTM D2457	%	90	
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm <sup>2</sup>	150
			lb/in <sup>2</sup>	21.800
		TD	N/mm <sup>2</sup>	280
			lb/in <sup>2</sup>	40.600
ELONGATION AT BREAK	ASTM D882	MD	200	
		TD	60	
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	3	
		TD	1	
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,60	
		Film/Metal	0,20	
SURFACE TENSION	ASTM D2578	Dyne/cm	Treated Side	38
			Other Side	-
HEATSEAL RANGE (*)	ASTM F88	°C	80 - 145	
		°F	176 - 293	
HEATSEAL STRENGTH (*) (80 °C, 1 MPa, 1 s)	ASTM F88	N/15mm	2,0	

### (\*) Low SIT surface

#### Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

**For related spec sheet with tolerance values, please contact our sales departments**