



SUPLAIN

1011 & 1011 A

Description

SUPLAIN 1011 & 1011 A are transparent, biaxially oriented polypropylene (BOPP) film. One side is treated with high adhesion property. No heat seal property.

Specially designed for excellent ink and adhesive adhesion due to high adhesion treated layer.

Designed to be used as single ply surface print and/or lamination substrate for different packaging and industrial applications. Can be also used as outer web release substrate for cold seal structures.

1011 A is specially designed for PSA tape applications where excellent adhesive and release lacquer bonding are required.

Properties

- Excellent mechanical and dimensional properties
- High gloss and clarity
- Excellent adhesion to inks and coatings
- Excellent adhesion to lamination adhesives with different substrates
- Resistance to chemicals, greases and oils
- Good moisture barrier
- Excellent adhesion to water and acrylic based adhesive coatings and hot melt adhesives
- The film shelf life is 6 months

Technical Features

PROPERTIES	TEST METHOD	UNITS	1011		1011 A		1011				
THICKNESS	ASTM F2251	micron	15	20	25	28	30	33	35	37	40
		Gauge	60	80	100	112	120	132	140	148	160
YIELD	ASTM D4321	m ² /kg	73,3	54,9	44,0	39,2	36,6	33,3	31,4	29,7	27,5
		in ² /Lbs	51.500	38.600	30.900	27.600	25.800	23.400	22.100	20.900	19.300
UNIT WEIGHT	ASTM D4321	g/m ²	13,7	18,2	22,8	25,5	27,3	30,0	31,9	33,7	36,4
HAZE	ASTM D1003	%	1,2		1,5		1,6				
GLOSS (45 °)	ASTM D2457	%	94								
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	150							
			lb/in ²	21.800							
		TD	N/mm ²	280							
			lb/in ²	40.600							
ELONGATION AT BREAK	ASTM D882	MD	180								
		TD	60								
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	3								
		TD	1								
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film	0,35								
		Film/Metal	0,20								
SURFACE TENSION	ASTM D2578	Dyne/cm	Treated Side	38							
			Other Side	-							

“Product Identification (Decision 97/129/EC): PP5”

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The film can also be supplied with ISCC+ certified raw materials with the category of bio-circular feedstock under the product group of SUPRENEW and category of circular feedstock under the product group of SUPCYCLE. SUPRENEW and SUPCYCLE products are certified with “Mass Balance” chain of custody system under ISCC+ and due to chemical processing of the feedstock, there is no compromise & change on any specific feature of the film given in this TDS regardless of the sustainable content in the film. Therefore all product properties of this film covers the same product code with SUPRENEW or SUPCYCLE brand. Three digits will be added to the end of the ISCC+ certified product code. SUPRENEW products will be differentiated with Rxx (R will communicate that the film is circular xx code will communicate the sustainable content % of the film) and SUPCYCLE products will be differentiated with Pxx (P will communicate that the film is circular xx code will communicate the sustainable content % of the film). Further details of the sustainable content of the film will be given in the Sustainability Declaration (SD) prepared for each ISCC+ certified order.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments

STANDARD ROLL DIMENSIONS			
CORE INNER DIAMETER (ID)	CORE OUTER DIAMETER (OD)	LENGTH TOLERANCE	WIDTH TOLERANCE
76 mm (3 in) & 152 mm (6 in)	530 mm & 790 mm *	± % 5 for ≤ 390 mm OD ± % 10 for > 390 mm OD	- 0 & + 4 mm

* 790 mm OD is available for BOPP films above 350 mm width

REV: 02 Date: 12.06.2025