



SUPEARL

1112 MP

Description

SUPEARL 1112 MP is a white opaque, cavitated, biaxially oriented polypropylene film with improved stiffness. No heat seal property. Both sides treated.

Lamination and cold seal applications where the temperature sensitive products are to be packed.

Any possible caution for blocking tendency during printing and/or other processes should be taken since the film is both sides treated.

Properties

- Moderate density and yield
- Excellent stiffness compared with cavitated films
- Outstanding opacity to prevent product show-through
- Good moisture barrier
- Paper replacement for decorative purposes
- Excellent UV light protection
- Excellent ink and cold seal adhesion

Technical Features

PROPERTIES	TEST METHOD	UNITS		1112 MP
THICKNESS	ASTM F2251	micron		40
		Gauge		160
YIELD	ASTM D4321	m ² /kg		33,3
		in ² /Lbs		23.400
UNIT WEIGHT	ASTM D4321	g/m ²		30,0
GLOSS (45 °)	ASTM D2457	%		75
LIGHT TRANSMISSION	ASTM D1746	%		25
OPACITY	DIN 53146	%		82
TENSILE STRENGTH AT BREAK	ASTM D882	MD	N/mm ²	80
			lb/in ²	11.600
		TD	N/mm ²	170
			lb/in ²	24.700
ELONGATION AT BREAK	ASTM D882	MD	%	100
		TD		40
THERMAL SHRINKAGE (120 °C, 5 min, air)	ASTM D1204	MD	%	3
		TD		1
COEFFICIENT OF FRICTION	ASTM D1894	Film/Film		0,35
		Film/Metal		0,20
SURFACE TENSION	ASTM D2578	Dyne/cm	Treated Side	38
			Other Side	38

Regulatory Status

Our product complies with the applicable EC legislation on packaging involving direct contact with foods except metallized films. Full details are given on the Regulatory Compliance Certificate and can be found on our web site.

The information contained in this data sheet is true and accurate according to current state of our knowledge and intended to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specific conditions of laboratory and/or actual use. We suggest our customers to determine final suitability for their specific end uses.

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departments